

NONLOGARITHMIC MAGNETIZATION RELAXATION AT THE INITIAL TIME INTERVALS AND MAGNETIC FIELD DEPENDENCE OF THE FLUX CREEP RATE IN $\text{Bi}_2\text{Sr}_2\text{Ca}_2\text{Cu}_2\text{O}_x$ SINGLE CRYSTALS.

V.V.Moshchalov*, A.A.Zhukov*, V.D.Kuznetsov⁺,
V.V.Metlushko⁺, L.I.Leonyuk*.

*Moscow State University, Moscow II7234, USSR, ⁺Moscow
Institute of Chemical Engineering, Moscow I25820, USSR.

At the initial time intervals, preceding the thermally activated flux creep regime, fast nonlogarithmic relaxation is found. The full magnetic moment $p_m(t)$ relaxation curve for $T=77\text{K}$, $B\parallel c$, $B=8,92\text{ mT}$ is shown in Fig.I. The magnetic measurements were made using SQUID-magnetometer. Two different relaxation regimes exist. For $t < t_0$ the relaxation is almost exponential as it is illustrated by the insert in Fig.I. Moreover, the $p_m(0)$ value is determined only by the external magnetic field. For large times $t > t_0$ the well known logarithmic dependence appears. It is shown by so-




Fig. I

This assumption correlates with our $p_m(t)$ measurements. The characteristic time t_0 separating two different relaxation regimes decreases as temperature and magnetic field are

lowered. The logarithmic magnetization relaxation curves $P_m(t)$ for fixed temperature $T_0 = 50, 0 \pm 0, 1$ K and different external magnetic field inductions B are given in Fig. 2. The B values are 1-2, 45 mT, 2 - 4, 51 mT, 3-7, 83 mT, 4-13, 84 mT, 5-18, 28 mT, 6-20, 22 mT, 7-52 mT.

The relaxation rate dependence on magnetic field, $R(B) = dP_m(B, T_0)/d(\ln t)$ has a sharp maximum which is similar to that found for $R(T)$ temperature dependences. The maximum shifts to lower fields as temperature goes up. The $R(B)$ dependences for $T_0 = 30$ K (curve 1) and $T_0 = 50$ K (curve 2) are shown in the insert in Fig. 2. The observed sharp maximum is related to a topological transition in shielding critical current distribution and, consequently, in Abrikosov vortices density. Taking into account the Anderson's thermally activated flux creep and the Abrikosov vortices distribution according to the Bean's model we have obtained curves shown in the insert in Fig. 2 by solid lines.

Summarizing, the nonlogarithmic magnetization relaxation for the initial time intervals is found. This fast relaxation has almost an exponential character. The sharp relaxation rate $R(B)$ maximum is observed. This maximum corresponds to a topological transition in Abrikosov vortices distribution.




Fig. 2